

ArcStar 111K3

AWS A5.29 E111T1-K3CJ

Characteristics and Applications:

ArcStar 111K3 offers excellent arc stability and low spatter with CO₂ shielding gas. It also has a fast freezing slag for all-position welding. These features, along with relatively low diffusible hydrogen levels, excellent slag removal, good impact values and high strength levels, make ArcStar 111K3 a superior choice for welding quench and tempered low alloy steels, such as ASTM A514, S690QL1 (EN 10025-6) etc.

Notes on usage:

1. Use (DC+) polarity.
2. Use 100%CO₂, 20~25 l/min shielding gas.
3. Control welding heat input is critical for getting essential impact value, since notch toughness tends to decrease under excessive heat input.
4. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%) :

	C	Mn	Si	P	S	Ni	Mo
AWS	≤0.15	0.75-2.25	≤0.80	≤0.030	≤0.030	1.25-2.60	0.20-0.65
Typical value	0.04	1.65	0.40	0.019	0.002	2.37	0.48

Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -40(-40°F)
AWS	≥ 680(98)	760-900(110-130)	≥ 15	≥ 27(20)
Typical value	735(107)	790(115)	22	50(37)

Welding position:



Sizes and recommended parameter range (DC <+>) :

Stick out: 15-25 (mm), gas flow rate: 20-25 (l/min):

Position	Diameter(mm)	1.2
F, HF		160A-300A/22V-34V
VU, OH		150A-220A/21V-26V
VD		250A-300A/26V-34V
H		200A-260A/23V-28V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.