

TFW-309L

AWS A5.22 E309LT1-1
EN ISO 17633-A-T 23 12 L P C 1 1
JIS Z 3323 TS309L-F C 1

Characteristics and Applications:

TFW-309L is designed for 100% CO₂ gas shielding and all position welding. It is commonly used for welding similar alloys in wrought or cast forms, or used in dissimilar welding, such as low alloy steel, heat-resistant steel and clad steel.

Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use 99.8% purity or higher CO₂ shielding gas.
3. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S	Cr	Ni
AWS	≤ 0.04	0.5-2.5	≤ 1.0	≤ 0.04	≤ 0.03	22.5-25.0	12.0-14.0
EN ISO	≤ 0.04	≤ 2.5	≤ 1.0	≤ 0.030	≤ 0.025	22.5-25.0	12.0-14.0
Typical value	0.026	1.40	0.55	0.021	0.008	24.07	12.78

Typical mechanical properties of weld metal:

	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -46°C (-51°F)
AWS	≥ 520 (75)	≥ 30	-
EN ISO	≥ 510 (74)	≥ 25	-
Typical value	546 (79)	36	42(31)

Welding position:



Sizes and recommended parameter range (DC <+ >):

Stick out:15-20(mm),flow rate:20-25(l/min):

Position	Diameter (mm)	1.2	1.6
	F, HF		150A-240A/25V-32V
H		140A-240A/25V-32V	180A-300A / 27V-35V
V-UP		130A-160A/24V-28V	160A-200A / 24V-28V
OH		150A-180A/25V-28V	-

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.