

# TFW-309LMo

AWS A5.22 E309LMoT1-1  
EN ISO 17633-A-T 23 12 2 L P C1

## Characteristics and Applications:

TFW-309LMo is a modified type of TFW-309L with the addition of molybdenum. It is suitable for joining stainless steels to unalloyed steels. The addition of molybdenum enhances creep strength and improves corrosion resistance.

## Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use 99.8% purity or higher CO<sub>2</sub> shielding gas.
3. Keep the product dry, while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S	Cr	Ni	Mo	Cu
AWS	≤ 0.04	0.5-2.5	≤ 1.0	≤ 0.04	≤ 0.03	21.0-25.0	12.0-16.0	2.0-3.0	≤ 0.75
EN ISO	≤ 0.04	≤ 2.5	≤ 1.2	≤ 0.030	≤ 0.025	22.0-25.0	11.0-14.0	2.0-3.0	≤ 0.5
Typical value	0.025	1.16	0.57	0.023	0.007	23.46	12.51	2.20	0.04

## Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %
AWS	-	≥ 520(75)	≥ 25
EN ISO	≥ 320(46)	≥ 550(80)	≥ 25
Tensile strength	590(86)	685(99)	33

## Welding position:



## Sizes and recommended parameter range ( DC <+> ):

Stick out:15-20(mm),flow rate:20-25(l/min):

Position	Diameter (mm)	1.2
F, HF		150A-240A/24V-32V
H		140A-180A/25V-32V
V-UP		130A-160A/24V-28V
OH		150A-180A/25V-28V

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.